

PRO-SET®

Technical Data

INF-117G

INF-2049

BIOBASED

INFUSION EPOXY

The New
Standard

EPOXIES for
Laminating
Infusion
Tooling
Assembly

**Wessex Resins
& Adhesives**

Cupernham House
Cupernham Lane
Romsey, Hampshire
SO51 7LF, UK
pro-set.co.uk
+44(0)1794 521111

ISO9001:2015 Certified

REV 3 / Sept 2022

©2022 Wessex Resins
& Adhesives

INTRODUCTION

The combination of PRO-SET INF-117G Resin with PRO-SET INF-2049 Hardener is intended specifically for resin infusion processes. This production technique has become increasingly important to the composite industry and has made inroads into the marine market for the manufacture of lightweight, high performance hulls together with the deck assemblies and superstructure.

PRO-SET INF-117G Resin is mixed with PRO-SET INF-2049 Hardener. The hardener is free of phenol and phenol related products - to produce an extremely low viscosity epoxy that provides fast and thorough wetting of the reinforcing fabric(s) within the laminate when using the resin infusion process.

CURING

The cure time will vary with the ambient temperature and the thickness of the laminate and, for example, at a working temperature of 20°C, vacuum pressure should remain on the laminate for at least 12 hours after infusion is complete.

The resin and hardener mix will initially cure to a brittle "B" stage after 24 hours at room temperature but laminate must be subsequently post cured at 50°C for 16 hours before demoulding the component.

HANDLING PROPERTIES

Property	Standard	Units	25°C
100g Pot Life	ASTM D2471	minutes	136
500g Pot Life	ASTM D2471	minutes	90
3mm thin film gel time		minutes	1375
Viscosity Mixed	ASTM D2196	mPas	220
Viscosity (resin)	ASTM D2196	mPas	480
Viscosity (hardener)	ASTM D2196	mPas	25

MIX RATIO

Method	Resin:Hardener	Resin:Hardener
Weight	2.94:1	100:34
Volume	2.44:1	100:41

DENSITY

State	Units	21°C
Mixed	gcm ⁻³	1.11
Resin	gcm ⁻³	1.17
Hardener	gcm ⁻³	0.96

Test specimens were neat epoxy (without fibre reinforcement).
Typical values not to be construed as specification

The biobased content of PRO-SET INF-117G resin is 36% as measured according to the ASTM D6866-18 test method.

INF-117G / INF-2049

BIOBASED INFUSION EPOXY

MECHANICAL PROPERTIES

Property	Standard	Units	RT x 24 hrs + 50°C x 16 hrs	RT x 24 hrs + 50°C x 16 hrs + 80°C x 2 hrs
Hardness	ASTM D2240	Shore D	82	83
Compression Yield	ASTM D695	MPa	86.8	85.4
Tensile Strength	ASTM D638	MPa	58.4	45.8
Tensile Modulus	ASTM D638	GPa	3	3
Tensile Elongation	ASTM D638	%	4.5	8.8
Flexural Strength	ASTM D790	MPa	96	88.4
Flexural Modulus	ASTM D790	GPa	4.4	4.1

THERMAL PROPERTIES

Property	Standard	Units	RT Gelation + 50°C x 16 hrs	RT Gelation + 50°C x 16 hrs + 80°C x 2 hrs
Tg DMA Peak Tan Delta	ASTM E1640*1	°C	74.2	83
Tg DSC Onset - 1st Heat	ASTM E1356	°C	52.6	56.6
Tg DSC Ultimate	ASTM E1356	°C	68.3*2	71.7*2

*1 1Hz, 3°C per minute.

*2 Additional post cure may be required; contact Technical Department for details.

Test specimens were neat epoxy (without fibre reinforcement).

These are typical properties and cannot be construed as a specification. The end users should test the products to ensure the products are suitable for the intended application. Any information, data, advice or recommendation published by Wessex Resins or obtained from Wessex Resins by other means and whether relating to Wessex Resins' materials or other materials, is given in good faith and believed to be reliable.

REV 3 / Sept 2022